



JSADD 3D Printing Service Provider

JSADD·3D



KS908C

Technical Data



Material Overview

KS908C is a brown color SLA resin for accurate and detailed parts. With fine textures, temperature resistance and good strength, KS908C is specially developed for printing shoe maquette/ shoe sole master models, and quick mold for PU sole, but it's also popular with dental, art & design, statue, animation and film.

Advantage

- > Highly accurate
- > Fine surface texture
- > Clear edges and corners
- > Good moisture resistance

Ideal Applications

- > Shoe models
- > Dental
- > Art and design
- > Statue
- > Animation film

Technical Datasheet

Liquid Properties		Optical Properties	
Appearance	Brown	Dp	0.135–0.155 mm
Viscosity	405–505 cps @ 28 °C	Ec	9 – 12 mJ/cm ²
Density	1.11–1.14g/cm ³ @ 25 °C	Building layer thickness	0.1–0.15mm

Mechanical Properties		UV Postcure
Measurement	Test Method	Value
Hardness, shore D	ASTM D 2240	74–80
Flexural modulus, Mpa	ASTM D 790	2,650–2,750
Flexural strength, Mpa	ASTM D790	60– 75
Tensile modulus, MPa	ASTM D638	2,150–2,370
Tensile strength, MPa	ASTM D 638	25–30
Elongation at break	ASTM D 638	12 –20%
Impact strength, notched Izod, J/m	ASTM D 256	58–70
Heat deflection temperature, °C	ASTM D 648 @66PSI	58–68
Glass transition, Tg, °C	DMA, E"peak	55–70
Density, g/cm ³		1.14–1.16

Recommended temperature for processing and storage of the above resin should be 18°C–25°C.

Shenzhen JSADD 3D Technology Co., Ltd.

Building B, No. 148 Huanli Road, Yungu Community, Xinhui Street,
Guangming District, Shenzhen, China.

 www.jsadditive.com

 info@jsadditive.com

 @ Vcauum Casting

 @JSADD 3D

 @JSADD.3D

 @jsadditive